

Material	Stahl N/mm ²				Rostfreie Stähle		Guss		NE-Metalle			Superleg.	Einsatzempfehlung		
	<500	<800	<1200 (<HRC38)	<1600 (<HRC48)	<800	<1200	GG	GGG	Al Knetleg.	Al Si<10%	Cu,Ms	Ti/Ni/Co <300	800-1500	HRC 48-57	HRC 58-63
Zugfestigkeit															
40 00 865 837 - Vc (m/min)	70-90	45-80	35-60		30-45	20-30	90	70	250	220	190				
Kühlung	Emulsion/Öl	Emulsion/Öl	Emulsion/Öl		Emulsion/Öl	Emulsion/Öl	Emulsion/Öl	Emulsion/Öl	Emulsion/Öl	Emulsion/Öl	Emulsion/Öl				

Fortsetzung >