

### Einsatzempfehlung

Material	Stahl N/mm <sup>2</sup>				Rostfreie Stähle		Guss		NE-Metalle			Superleg.	Stahl gehärtet		
Zugfestigkeit	<500	<800	<1200 (<HRC38)	<1600 (<HRC48)	<800	<1200	GG	GGG	Al Knetleg.	Al Si<10%	Cu, Ms	Ti/Ni/Co <900	900-1500	HRC 48-57	HRC 58-63
40 00 867 343 - Vc (m/min)	28	23	16	12	15	12	24	20	50	30	20				
Kühlung	Emulsion/Öl	Emulsion/Öl	Emulsion/Öl	Emulsion/Öl	Emulsion/Öl	Emulsion/Öl	Emulsion/Öl	Emulsion/Öl	Emulsion/Öl	Emulsion/Öl	Emulsion/Öl				